

## VISION Rechargeable Products Sealed Lead Acid Battery

www.vision-batt.com

## **HP&HF** Series

#### **High Rate Discharge**

The new VISION HP/HF series batteries are specially designed for applications where need high power output. By optimum design of battery grids and plate paste formula, the HP/HF series can deliver up to 40% more power than VISION standard CP/FM series.

Shenzhen Center power tech co., Itd has more than 15 year's experience in the manufacturing of VRLA batteries.

SZCPT is one of the biggest manufacturers of SLA (or VRLA) batteries in the world, the biggest one in Mainland China and the first in China to develop and commercialize the sealed lead-acid battery with brand name VISION and has been at the forefront of battery technology from day one.

SZCPT leads the world in innovative battery technology. Our global network of sales and service engineers, backed in turn by our agents and distributors, means that we are currently active in more than 100 countries.

Shenzhen Center Power Tech. Co., Ltd

#### HF12-155W-X 12V28Ah

#### **General Features**

- Positive and negative plates in lead-calcium tinalloy
- Superior energy density
- Operates at a low internal pressure.
- Gas Recombination
- Usable in any orientation
- A recognized component of UL

- Very high power output
- Application specific designs
- A couple Range from 13W to 890W per cell for 10' @ 1.60Vpc

(Edition June 2004)

- Six months shelf life at 20°C
- Design life 10 years





Dimensions and Weight												
	SI Units	English Units										
Length	165mm	6.50inch										
Width	125mm	4.92inch										
Height	175mm	6.89inch										
Total Height	175mm	6.89inch										
Approx. Weight	9.60Kg	21.2lbs										

#### **Performance Characteristics**

- Nominal Voltage 12V
- Number of cell 6
- Nominal Capacity 68°F(20°C)

10 min wattage @1.6V155W/cell 20 hour rate (1.40A, 10.5V) 28.0Ah

Nominal Capacity 77°F(25°C)

10 hour rate (2.70A, 10.8V) 27.0Ah

Internal Resistance

Fully Charged battery 68°F(20°C) 6.7mOhms

Self-Discharge

3% of capacity declined permonth at 20°C(average)

Operating Temperature Range

Discharge -20~60°C

Charge -10~60°C

Storage -20~60°C

Max. Discharge Current 68°F(20°C) 310A(5s)

■ Charge Methods: Constant Voltage Charge 68°F(20°C)

Cycle use 14.5-14.9V

Maximum charging current 8.4A

Temperature compensation -30mV/°C

Standby use 13.6-13.8V

Temperature compensation -20mV/°C









Center Power Industrial Park, Tongfu Industrial District Dapeng Town, 518120 Shenzhen, China Tel: 86 755 84318088 Fax: 86 755 84318038 E-mail: sales@vision-batt.com Website: http://www.vision-batt.com

## HF12-155W-X 12V 28Ah

## Discharge Data

	Constant Current Discharge Data (Amperes at 25°C)																								
End voltage volts/cell	5min	10min	15min	20min	25min	30min	35min	40min	45min	50min	55min	60min	1.5h	2h	2.5h	3h	4h	5h	6h	7h	8h	9h	10h	12h	24h
1.60	125	87.5	67.3	54.5	46.8	41.7	36.5	32.6	29.6	27.2	25.2	23.5	16.4	12.9	10.7	9.30	7.20	5.94	4.99	4.31	3.81	3.41	3.10	2.64	1.35
1.65	117	82.7	63.8	51.7	44.4	39.6	34.7	31.0	28.1	25.9	24.0	22.4	15.7	12.3	10.3	8.90	6.90	5.70	4.79	4.14	3.66	3.28	2.98	2.54	1.31
1.70	110	78.0	60.3	48.9	42.0	37.4	32.8	29.4	26.7	24.6	22.8	21.4	14.9	11.7	9.80	8.51	6.60	5.46	4.59	3.97	3.51	3.15	2.86	2.45	1.25
1.75	103	73.2	56.8	46.1	39.6	35.3	31.0	27.8	25.3	23.3	21.6	20.3	14.2	11.2	9.32	8.11	6.30	5.21	4.39	3.80	3.36	3.02	2.74	2.35	1.19
1.80	98.2	70.5	54.8	44.6	38.5	34.4	30.2	27.1	24.7	22.7	21.1	19.8	13.9	10.9	9.14	7.95	6.18	5.12	4.31	3.74	3.31	2.97	2.70	2.32	1.17

	Constant Power Discharge Data(Watts per cell at 25°C)																								
End voltage volts/cell	5min	10min	15min	20min	25min	30min	35min	40min	45min	50min	55min	60min	1.5h	2h	2.5h	3h	4h	5h	6h	7h	8h	9h	10h	12h	24h
1.60	229	155	118	95.3	81.7	72.6	64.6	58.6	53.9	49.7	46.3	43.5	30.5	24.1	20.2	17.6	13.7	11.4	9.64	8.39	7.45	6.72	6.13	5.26	2.75
1.65	219	149	114	92.1	79.0	70.3	62.6	56.8	52.3	48.3	45.0	42.3	29.7	23.4	19.7	17.2	13.4	11.2	9.44	8.21	7.29	6.58	6.01	5.17	2.71
1.70	210	144	110	89.0	76.3	67.9	60.5	55.0	50.7	46.8	43.7	41.1	28.9	22.8	19.1	16.7	13.1	10.9	9.23	8.03	7.14	6.44	5.89	5.08	2.66
1.75	200	138	106	85.8	73.6	65.6	58.5	53.2	49.0	45.4	42.4	39.9	28.1	22.2	18.6	16.3	12.8	10.7	9.02	7.86	6.99	6.31	5.76	4.98	2.62
1.80	190	132	102	82.6	71.0	63.2	56.4	51.4	47.4	43.9	41.1	38.7	27.3	21.5	18.1	15.8	12.4	10.4	8.81	7.68	6.83	6.17	5.64	4.89	2.57

(Note) The above characteristics data are average values obtained within three charge/discharge cycles not the mimimum values.

# Performance Drawings











